



Test Report No. F690101/LF-CTSAYSA19-23722

Issued Date: 2019. 10. 28

Page 1 of 3

ARTBEBE

203-1, Gusang-gil, Waegwan-eup,
Chilgok-gun, Gyeongsangbuk-do,
Korea

The following sample(s) was/were submitted and identified by/on behalf of the client as:-

SGS File No.	: AYS19-23722
Sample Description	: ONE SAMPLE OF 100 % POLYESTER ECHO BAG WOVEN FABRIC
Color	: WHITE, BLUE GREEN, RED
Style no./Item no.	: N/A
Order No.	: N/A
Country of Origin	: KOREA
Country of Destination	: N/A
Proposed care Instruction	: N/A
Received Date	: 2019. 10. 22
Test Period	: 2019. 10. 22 to 2019. 10. 28
Purpose of Test Report	: For Self Reference
Test Method	: Please refer to next page(s).
Test Results	: Please refer to next page(s).
Report Comments	: The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This test report is not related to Korea Laboratory Accreditation Scheme.
Result summary	: Selected test(s) as requested by client

SGS Korea Co., Ltd.

Daesung Lee / Technical Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com/en/terms-and-conditions/terms-e-document>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s).

CQP-7081-F18 (01)

SGS Korea Co., Ltd.

322, The O valley, 76, LS-ro, Dongan-gu, Anyang-si, Gyeonggi-do, Korea 14117
t +82 (0)31 4608 000 f +82 (0)31 4608 059 <http://www.sgsgroup.kr>



Test Report No. F690101/LF-CTSAYSA19-23722

Issued Date: 2019. 10. 28

Page 2 of 3

Test Conducted

Results

Color Fastness to Rubbing, Grade

Test Method: ISO 105-X12:2016, (Long direction: oblique, Download force: (9 ± 0.2) N)

Size of rubbing finger: 16 mm dia.

Dry	4-5
Wet	4-5

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

Color Fastness to Water, Grade

Test Method: ISO 105-E01:2013

Color change	4-5
Stain (Acetate)	4
(Cotton)	4
(Nylon)	3-4
(Polyester)	4
(Acrylic)	4-5
(Wool)	4-5
Self-Staining	5

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

Color Fastness to Light, Grade

Test Method: ISO 105 B02: 2014 Method 3 Modified; Xenon-Arc Lamp in exposure cycle A1 / no flip-flop mode was used

Color change	Over 4
<Note> Blue Scale Standard	

Tensile Strength, N

Test Method: ISO 13934-1:2013, Strip Method

Warp	5200
Weft	2900

Water Resistance - Rain Test, g

Test Method : ISO 22958 : 2009

Water penetration

1 st	0.1
2 nd	0.1
3 rd	0.1

<Note> Test was conducted under a hydrostatic head of 2 feet (600 mm) for a period of 5 minutes.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com/en/terms-and-conditions/terms-e-document>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s).

CQP-7081-F18 (01)

SGS Korea Co., Ltd.

322, The O valley, 76, LS-ro, Dongan-gu, Anyang-si, Gyeonggi-do, Korea 14117
t +82 (0)31 4608 000 f +82 (0)31 4608 059 <http://www.sgsgroup.kr>

Member of the SGS Group (Société Générale de Surveillance)

Picture of Sample as Received :



AYSA19-23722

*** End of Report ***