



Manufacturing Plant
SOLVAY SILICA KOREA CO., LTD.
22194,SOUTH KOREA,INCHEON,
DOKBAE-RO, NAM-GU 267
(HAGIK-DONG)

SOLVAY SILICA KOREA CO., LTD.
(HAGIK-DONG)
267 DOKBAE-RO, NAM-GU
,INCHEON,SOUTH KOREA,22194

JUNGWOO CHEMICAL CO., LTD.
291 ILSANDONG-GU JANGHANG-RO
,GOYANG-SI,SOUTH KOREA,10431

Certificate of analysis

Print date:
19.Jan.2017
Purchase order item/Date
JW170119 10 / 18.Jan.2017
Delivery item/Date
83508861 900002 / 19.Jan.2017
Order item/Date
2210879 000010 / 19.Jan.2017
Customer
82099
Truck number/Seal number
6596/

Material: Our / Your reference
105831 TIXOSIL 73 PP BAG 15KG EXP /

The dispatched material conforms to agreed requirements

Batch K7A12A1011, Manufacturing date 12.Jan.2017, Expiry date 12.Jan.2019, Quantity 2.910 TO

Characteristic	Unit	Value	Lower Limit	Upper Limit	Method
pH (5%-suspension)		7.5	7.2	8.2	G07Q-018
Soluble Salts(as Na ₂ SO ₄)	%	0.8	-	1.5	G07Q-017
Ignition loss at1000'C(TGA,after drying)	%	3.9	-	8.5	G07Q-015
Moisture loss at 105'C(TGA, 2hrs)	%	4.4	0.0	7.0	G07Q-015
Oil absorption DOA	ml/1hg	109	105	125	G07Q-016
Wet sieve residue 45µm	%	0.1	-	1.5	G07Q-013
Av.size(LASER:D50)	µm	10.6	6.0	12.0	G07Q-032
F-Compatibility	%	98	90	-	G07Q-038
Transmission (UV)	%	75	60	-	G07Q-036
Refractive Index		1.440	1.437	1.447	G07Q-036

Jong-Ho.KIM
Quality Control Laboratory Manager
e-mail:Jong-Ho.KIM@solvay.com
tel) +82 32 8706 114