

# CJ O SHOPPING TEST REPORT

KOTITI No. | 82191048103300

To | 스카이 트립

Date In | SEP 02, 2019

Date Out | SEP 05, 2019

## OVERALL RATING

PASS ☐

FAIL ☒ V

N / A ☐

Title	Test Report
Item	Test(other)
Item Name	POUCH
Buyer	CJ O SHOPPING
Brand Name	N/S
Style Number	ST-3TP
PO Number	N/S
Related(FO, FP) Report No	N/S
Color	(A)GREY
Submitted Fiber Composition	N/S
Recommended Fiber Composition	N/A
Submitted Care Instruction	HAND WASH
Recommended Care Instruction	N/A
Test Result	For further details, please refer to the following page(s).

Affirmation	Prepared by Name : Myung Ji Ko	Technical Manager Name : Chae Hong Kim
-------------	-----------------------------------	---

**KOTITI** Testing & Research Institute



111, Sagimakgol-ro, Jungwon-gu, Seongnam-si, Gyeonggi-do, Korea T (822)3451-7000 F (822)3451-7177 W www.kotiti-global.com

1. The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products.
2. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the KOTITI Testing & Research Institute.
3. The test result in this report is not related to accreditation of KOLAS.
4. You can verify the authenticity by the QR code at the bottom right side of the issued report, or access <http://cs.kotiti-global.com> and enter the test report number.



# SUMMARY

Individual Test Item	PASS	FAIL	REMARK
Water Repellency(Spray Test)	V		
Water Resistance (Rain Test)		V	(A)

**Contact Information for technical questions and general inquiries.**

·Primary Contact : Eun Ji Jo    T (822)6191-6151   E ejjo@kr.kotiti-global.com    ·Back-up : Chae Hong Kim    T (822)3451-7066   E chkim@kr.kotiti-global.com

**Water Repellency(Spray Test), Grade  
(KS K ISO 4920:2014)**

Test Conducted	Test Results	Requirements
(A)		
As Received(1st)	4.5	≥4
As Received(2nd)	4.5	
As Received(3rd)	4.5	
After 3 Washing(1st)	4	≥2
After 3 Washing(2nd)	4	
After 3 Washing(3rd)	4	

Note) Reference) Washing Condition: Hand wash ( $30 \pm 3$ )°C, Line dry, 3 Washes , KS K 0021:2011/ KS K ISO 6330:2012

**Water Resistance (Rain Test), g  
(KS K ISO 22958:2012, 2 minutes @ 600 mm)**

Test Conducted	Test Results	Requirements
(A)		
As Received(1st)	> 5	
As Received(2nd)	> 5	
As Received(3rd)	> 5	
After 1 Washing(1st)	> 5	
After 1 Washing(2nd)	> 5	
After 1 Washing(3rd)	> 5	

Note) Reference)Washing Condition:Hand wash ( $30 \pm 3$ ) °C, Line dry, 1 Washes, KS K 0021/2018 KS K ISO 6330: 2012

- End of Report -

**Photo of the submitted sample(s)**

